




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 03/12/2025 - 03/19/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	100-100	
#8 (2.36mm)	6	100	0.0	100-100	
#16 (1.18mm)	6	100	0.0	97-100	
#30 (.6mm)	6	97	1.5	80-100	
#50 (.3mm)	6	66	6.6	43-85	
#100 (.15mm)	6	6	0.6	0-25	
#200 (75µm)	6	0.1	0.05		
Pan	6	0.0	0.00		
FM	6	1.31	0.081		
Grad Loss	6	0.000	0.0000		
Total Moisture	6	3.0	0.50	0-5	0-6
D10 (ES)	6	0.16	0.000		
D50	6	0.25	0.015		
D60	6	0.28	0.018		
D15/D85	6	0.37	0.026		
Cu	6	1.79	0.110		



Query

Query Selections

Date Created 03/19/2025

Date Range 03/12/2025 - 03/19/2025

Plant Ortona Sand Company (FDOT Pit # 05-045)

Sample Type Shipping