




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 04/11/2025 - 04/18/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	13	100.0	0.00	95-100	
#8 (2.36mm)	13	99.9	0.04	85-100	
#16 (1.18mm)	13	96.7	0.55	65-97	
#30 (.6mm)	13	74.1	1.81	25-75	
#50 (.3mm)	13	38.8	3.24	5-40	
#100 (.15mm)	13	3.5	0.51	0-7	
#200 (75µm)	13	0.1	0.16		
Pan	13	0.0	0.00		
FM	13	1.87	0.046	1.82-2.18\2	1.8-2.2
Grad Loss	13	0.029	0.0569		
Total Moisture	13	3.6	0.51	1-5	1-5
D10 (ES)	13	0.1706	0.00281		
D50	13	0.37	0.018		
D60	13	0.45	0.019		
Cc	13	0.83	0.038		
Cu	13	2.66	0.078		



Query

Query Selections

Date Created 04/18/2025

Date Range 04/11/2025 - 04/18/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping