




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 04/11/2025 - 04/18/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	95-100	
#30 (.6mm)	4	99	0.5	85-100	
#50 (.3mm)	4	93	0.0	35-90	
#100 (.15mm)	4	11	4.9	3-35	
#200 (75µm)	4	0.1	0.05		
Pan	4	0.0	0.00		
FM	4	0.97	0.052	0.9-1.4	1.2
Grad Loss	4	-0.007	0.0140		
Total Moisture	4	3.4	0.19	0-5.5	0-6
D10 (ES)	4	0.1360	0.02047		
D50	4	0.21	0.005		
D60	4	0.22	0.006		
Cc	4	1.02	0.110		
Cu	4	1.70	0.226		



Tests: 1 D10(ES): 0.141 D15: 0.155 D30: 0.176 D50: 0.209 D60: 0.227 D85: 0.280 D90: 0.292 Cu: 1.613 Cc: 0.971

Query

Query Selections

Date Created 04/18/2025

Date Range 04/11/2025 - 04/18/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping