




# Basic Quality Statistical Summary Report

**Plant** 1210-Savannah Sand Mine  
**Product** 117-GDOT 10NS Concrete Sand  
**Specification** GADOT 10NS  
**Period** 04/11/2025 - 04/18/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
3/8" (9.5mm)	8	100.00	0.000		
#4 (4.75mm)	8	99.48	0.152		95-100
#8 (2.36mm)	8	93.68	0.516		
#16 (1.18mm)	8	75.69	2.190		45-95
#30 (.6mm)	8	45.57	4.025		
#50 (.3mm)	8	18.58	3.965		5-30
#100 (.15mm)	8	4.46	1.903		0-10
#200 (75µm)	8	0.21	0.151		0-3
Pan	8	0.00	0.000		
FM	8	2.62	0.118	2.4-2.85\2.65	
Grad Loss	8	0.000	0.0000		
Total Moisture	7	4.7	2.12	0-5\4	0-6
D10 (ES)	8	0.20	0.022		
D50	8	0.66	0.058		
Cu	8	4.14	0.295		



Tests: 1 D10(ES): 0.197 D15: 0.252 D30: 0.402 D50: 0.663 D60: 0.830 D85: 1.689 D90: 2.048 Cu: 4.214 Cc: 0.991

**Query**

Query Selections  
Date Created 04/18/2025  
Date Range 04/11/2025 - 04/18/2025  
Plant Savannah Sand Mine  
Sample Type Shipping